



L&M™ SEAL HARD®

DS-174.6-0724

**Globally Proven
Construction Solutions**



1. PRODUCT NAME

L&M™ SEAL HARD®

2. MANUFACTURER

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 1235

Toll Free: 1.800.243.4788, ext. 1235

Fax: +1.203.393.1684

Website: laticrete.com

3. PRODUCT DESCRIPTION

SEAL HARD is a concrete densifier that increases the strength of the wear surface of concrete floors subjected to pedestrian and vehicle traffic. SEAL HARD penetrates concrete to seal, dustproof, densify, and harden the surface and reduce absorptiveness. SEAL HARD floors increase the service life of concrete floors and resist dusting for years after application. SEAL HARD leaves no film and will not alter the natural, high traction texture of the concrete floor. Additionally, SEAL HARD treated floors provide a significant savings in maintenance costs over conventional acrylic, epoxy, and urethane sealers.

Specification Description

033000: Concrete densifier, sealer, hardener. All exposed concrete surfaces to be treated to harden, seal and densify exposed concrete. When applied by an Approved Applicator – a special 10 year, anti-dusting warranty is available. For additional information, please go to www.laticrete.com.

Uses

- SEAL HARD is a premium densifier that can be used in areas that would benefit from this process including floors subjected to medium or heavy fork lift and tow motor traffic; including those found in warehouses, distribution centers, food processing plants, breweries, and most concrete floors needing rehabilitation.
- Other uses include concrete floors subjected to frequent or heavy pedestrian traffic, such as: civic centers, retail sales outlets, discount stores, restaurants, food preparation areas, sports arenas, stadiums, hospitals, airports, museums, schools and grocery stores.

Advantages

- Dramatic long-term maintenance cost reduction
- Non-slip, certified high traction
- Zero VOC/ Odorless
- Formulated to resist dusting
- Creates a protective hardened and sealed surface
- USDA Compliant (FDA/CFSAN U.S. Food Code 6.101.11 Surface Characteristics)

Suitable Substrates

- Concrete

Packaging

5 Gal (18.9 L)

55 Gal (208 L)

Approximate Coverage

200 ft² gal (4.9 m²/L)

Additional coats may be necessary under certain porous conditions.

Apply second coat after first coat has completely dried.

Second coat: 350 ft² gal (8.6 m²/L)

Shelf Life

Containers are to be stored in a clean, dry area between 40-100°F (4-38°C). Shelf life of unopened containers is two years if properly stored. Do not allow to freeze.

Limitations

- Apply when temperatures are above 40°F (4°C)

- Not recommended for long term exposure to strong acid or severe chemical attack
- Apply only to structurally sound concrete surfaces. Not effective on porous or worn concrete
- Variations in concrete finishing and concrete mixes may cause variances in appearance of the SEAL HARD finish
- Not for use as a curing compound
- Will not hide existing staining or wear patterns in concrete
- For Professional Use Only

Cautions

- Please refer to the Safety Data Sheet (SDS) for safety information.
- Any floor can be slippery when wet or contaminated with foreign material. Promptly clean up spills and foreign materials
- Keep from freezing
- Wear protective gloves and goggles
- Avoid prolonged skin contact and absolutely no contact with all food stuffs
- Absolute minimum cure time for fresh concrete is 3 days before SEAL HARD® application. Waiting at least 7 days for new concrete to cure is recommended for best results before SEAL HARD application.
- Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to color, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

4. TECHNICAL DATA

Applicable Standard

- ASTM C642

Physical Properties

Property	Observed
Abrasion Resistance (ASTM C779)	225% Increased Wear Resistance
Skid Resistance (NFSI Standard 101.A)	High Traction
Static Coefficient of Friction Wet or Dry	>0.6
Moisture Absorption, ASTM C642 % reduction in 24 hours	81%
Surface Breathable	Yes
UV Stable	Excellent
Color	Clear
VOC g/L	0.0

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

5. INSTALLATION

- **Preparation of Existing Floors:** All sealers, paints, wax, coatings, floor coverings and their mastics, as well as any surface contaminants such as oil or food spills must be removed. Non-moving cracks and saw cut, control joints are to be routed, and cleaned. They will be filled later with rapid curing JOINT TITE 750™ or L&M™ FAST FIX™ products after the final steps of the process. Moving cracks must be addressed separately. Repair large or deep surface irregularities with L&M DURACRETE.

Preparation of New Floors: New concrete should be finished to a hard trowel finish per ACI-302.1R- 8.6.1. Note that SEAL HARD is not a curing compound. New concrete floors must be properly cured for a minimum of 3 days. Remove all surface sealers and film forming curing compounds. Sealers and curing compounds can be removed with CITREX™ or other approved non-acid cleaner before installation of SEAL HARD.

Application: Installation requires the use of an automatic floor scrubber or other mechanical equipment utilizing soft scrubbing pads. Apply a saturating coat directly from container. Aggressively scrub into the surface with a mechanical auto scrubber. Scrubbing will help achieve maximum penetration. Do not use metallic brushes. In hot weather, pre-dampen concrete surfaces with water to cool. After standing water dissipates, apply SEAL HARD.

Keep surfaces wet with SEAL HARD for 30 minutes and continue scrubbing. When product begins to thicken, sprinkle with water and continue scrubbing for another 10-15 minutes. Immediately wash off over-spray from glass, aluminum, or highly polished metal surfaces with water to avoid etching of the surfaces.

Do not allow product to dry before flushing excess from surfaces. Next, thoroughly flush excess SEAL HARD with clean water and remove all solution from the floor by squeegee and wet vacuum.

If SEAL HARD residue is not thoroughly washed and removed from floor, excess residue will dry as an unsightly white film or stain. Floor may be placed into service immediately after removal of the rinse residue. Rinse residue is non-hazardous and may be flushed into sanitary

sewer. After the residue is removed, dry time is approximately two to four hours. Additional coats may be necessary under certain porous conditions. Apply another coat [approx. 350 ft² gal (8.6 m²/L)] after first coat has been cleaned, rinsed, and is completely dried.

Approved Applicators - For best results, LATICRETE has trained and approved various SEAL HARD applicators throughout the U.S. and recommends their use. To find one near you, please contact LATICRETE Technical Services.

6. AVAILABILITY AND COST

Availability

LATICRETE materials are available worldwide.

For Distributor Information, Call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at

laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

7. WARRANTY

See 10. FILING SYSTEM:

- 1 Year Product Warranty (US) (English)

8. MAINTENANCE

The long term performance, appearance, and life expectancy of wear surface products are critically dependent upon a good routine maintenance program designed specifically for the installed wear surface type, traffic, and other conditions. Properly placed walk-off mats, inside and outside will help increase the life of the floor. Some cleaning products and equipment or improper use of products can damage a wear surface appearance over time. Recommended maintenance program consists of frequent and thorough cleanings utilizing FGS CONCRETE CONDITIONER™. Frequency of washing will vary, as it may be necessary daily, weekly or less frequently depending on floor usage and age. A mechanical walk-behind or ride-on scrubber is an efficient and economical means of regularly cleaning concrete floors. Only soft scrubbing or soft brush attachments should be used when mechanically scrubbing your floor. Do not use aggressive abrasive pads or brushes. The use of black scrubbing pads, diamond impregnated pads or carbide impregnated type brushes may dull the surface gloss. Wet mops work well

on small floors or places where a mechanical scrubber will not fit.

9. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 1235

Telephone: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at laticrete.com.

10. FILING SYSTEM

Additional product information is available on our website at laticrete.com. The following is a list of related documents:

- DS 230.13: LATICRETE Product Warranty
- DS 176.5: JOINT TITE 750™
- DS 176.6: CITREX™
- DS 177.1: FGS CONCRETE CONDITIONER™

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.