



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

October 7, 2024

PROSOL SALES AND DISTRIBUTION LTD
14-16 Gleadless Road
Sheffield, S2 3AB, UK

Reference: Laboratory Test Report
Lab Identification No. 61698
Invoice No. 92997

Dear Sir or Madam:

One (1) fabric sample, identified as **LBB6143**, was received and tested in accordance with ASTM D 6413-22, "Standard Test Method for Flame Resistance of Textiles (Vertical Test)". The results are as follows:

Test Results

Specimen Number	After Flame (seconds)		After Glow (seconds)		Char Length (inches)	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	3.2	0.0	0.4	0.2
2	0.0	0.0	0.0	0.0	0.2	0.2
3	0.0	0.0	9.3	0.0	0.6	0.3
4	0.0	0.0	0.0	0.0	0.2	0.2
5	<u>0.0</u>	<u>0.0</u>	<u>0.0</u>	<u>0.0</u>	<u>0.3</u>	<u>0.3</u>
Avg	0.0	0.0	2.5	0.0	0.3	0.2

Note: There were no occurrences of melting or drippings.

Sincerely,

Brian S. Dement

BSD/mr

