

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 6233

Data Sheet

Product Description

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 6233 is a one-part, heat curable, thermosetting epoxy coating powder designed for corrosion protection of pipe.

Properties

Property	Value
Specific Gravity	
Film	1.36
Powder	1.44
Coverage based on film	141 ft ² /lb/mil (0.735 m ² /kg/mm)
Color	Govt. Color 14272/Green
6233-4G	
Gel Time @ 400°F/205°C	9.5 seconds ± 20%
Cure Time @ 450°F/232°C	30 seconds
6233-8G	
Gel Time @ 400°F/205°C	17 seconds ± 20%
Cure Time @ 450°F/232°C	90 seconds
6233-11G	
Gel Time @ 400°F/205°C	25 seconds ± 20%
Cure Time @ 450°F/232°C	110 seconds
Shelf life @ 27°C/80°F	12 months

Temperature Operating Range

The Scotchkote 6233 coating, when properly applied, should perform in a satisfactory manner on pipelines operating between -100°F/-73°C to 230°F/110°C. For temperatures between +170°F/77°C to 230°F/110°C, laboratory tests indicate that the thicker coatings may improve the service capability. However, it is difficult to accurately predict field performance from the laboratory data due to the wide variation in actual field conditions. Soil types, moisture content, temperatures, coating thickness and other factors specific to the area all influence the coating performance and the upper temperature operating limit.

Scotchkote 6233 meets the requirements of AWWA C213 and C550.

3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 6233 Test Data

Property	Test Description			Typical Value
Impact	ASTM G14 (modified) 1/8 in (3.2 mm) thick plate 3/8 in (9.5 mm) thick plate			160 in•lbs (18.1 J) 59 in•lbs (6.7 J)
Cathodic Disbondment	CAN/CSA-Z245.20-12.8 48 hours, 1.5 volt, 3% NaCl 149°F/65°C 28 day, 1.5 volt, 3% NaCl 73°F/23°C 28 day, 1.5 volt, 3% NaCl 149°F/65°C			2.3 mm r 2.5 mm r 4.9 mm r
Hot Water Resistance	24 hours, CAN/CSA-Z245.20-12.14, 203°F/95°C 48 hours, CAN/CSA-Z245.20-12.14, 167°F/75°C			1 rating 1 rating
Bendability (Mandrel Bend)	<u>Temperature</u> 73°F/23°C -22°F/-30°C	<u>Pipe Diameters</u> <10.5 <19.1	<u>°/PD</u> 5.5 >3.0	<u>% Elongation</u> 4.8 >2.6
Compressive Strength	ASTM D 695			>10,000 psi (705 kg/cm ²)
Penetration	ASTM G 17 -40° to 200°F/-40° to 93°C			0
Thermal Shock	-320° to 310°F/-195° to 154°C Coated pipe			No visible effects 10 Cycles
Dielectric Strength	1180 V/mil/46 kV/mm			

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications.



Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid, Material Safety Data Sheet, and/or product label prior to handling or use.

3M and Scotchkote are trademarks of 3M Company.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture for a period of 12 months from the date of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether indirect, special, incidental or consequential regardless of the legal theory asserted.**



Corrosion Protection Department

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/corrosion

Please recycle. Printed in USA.
© 3M 2008. All rights reserved.
80-6111-8339-5-F

Ordering Information/Customer Service

For ordering technical or product information, or a copy of the Material Safety Data Sheet, call:

Phone: 800/722-6721 or 512/984-9393

Fax: 877/601-1305 or 512/984-6296