

Sterling Lead-Free

WOR: 331755

- Lowest melting temperature: 410° F
- Best flowing lead-free solder available
- Highest tensile strength: 7130 psi
- NSF 61 Certification – safe use in potable water applications
- Completely free of antimony and nickel



WOR Prod. No.	LENOX Prod. No.	Description	Weight		Diameter	
			lb	g	in	mm
331755	WS15086	Sterling Wire Spool	1	454	.118	3
331842*	WS15086NB*	Sterling Wire Spool	1	454	.118	3
331841	WS15259	Sterling Wire Spool	1	454	.118	3
331843	WS15084	Sterling Wire Spool	1	454	.062	1.6
331897	WS15090	Sterling Wire Spool	1/4	113	.118	3
331896	WS15092	Sterling Wire Spool	1/2	227	.118	3
331898	WS15091	Sterling Wire Spool	5	2270	.118	3
331895	WS15284	Sterling Wire Spool	5	2270	.062	1.6
331899	WS15081	Sterling Sm Ingot	5	2270		

* Spool is not sold in an individual box