



TECHNICAL DATA

CDL-61

UC-190 SRX URETHANE CEMENT

DESCRIPTION AND USES

Citadel® UC-190 SRX Urethane Cement is a heavy duty, self-leveling, slurry-broadcast, anti-slip and antimicrobial treated cementitious urethane flooring system.

The UC-190 SRX product is typically installed by factory trained contractors. Be sure you are fully aware of all application procedures and have all the required equipment available prior to beginning the installation of this product.

PRODUCT FEATURES AND BENEFITS

- 40 sq ft/unit at 3/16" (yielding a 1/4" finished floor)
- 30 sq ft/unit at 1/4" (yielding 5/16" finished floor)
- VOC <10 g/l, SCAQMD Approved
- Contains a silver ion antimicrobial additive to protect the surface
- Positively textured profile to minimize slip risks in wet or damp areas
- Resistant to temperatures of up to 250°F and suitable for steam cleaning
- Unaffected by moisture vapor transmission
- Rapid return to service in 24 hours
- Low odor and non-toxic
- This coating complies with USDA FSIS regulatory sanitation performance standards for food establishment facilities

PRODUCT

SKU	DESCRIPTION
400153	UC-190 SRX 40 sq. ft. Kit
400162	UC-190 SRX Filler (55 lb. Bag)

Kit Contents:

Part A - Base (1.188 Gal.), Part B - Hardener (0.979 Gal.).
Pigment, aggregate, and filler sold separately.

COMPANION PRODUCTS

SKU	DESCRIPTION
400157	UC Grey Pigment Pack
400158	UC Red Pigment Pack
400160	UC Dark Grey Pigment Pack
314759	#20-40 Silica Sand (50 lb. bag)

RECOMMENDED TOPCOATS

- Citadel RG-70
- Citadel RG-80
- Citadel UL-80
- Citadel ET-80
- Citadel PLE-100
- Citadel SLE-100

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

NEW CONCRETE: New concrete should be allowed to cure for a minimum of 28 days. The concrete must be structurally sound, dry, and free of grease, oils, dust, curing compounds and other coatings or contaminants. Surface laitance must be removed. The preferred method of surface preparation is to mechanically abrade the floor by diamond grinding to achieve a final 60-80 grit finish, reference profile CSP-5 according to ICRI. If patching is required, use Citadel Fortification Formula Concrete Repair.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding or sweep blasting to create a surface profile. The UC-190 SRX is compatible with most coatings, but a test patch is suggested.

NOTE: Concrete should have a minimum of 3,000 psi compressive strength. Concrete must be visibly dry at time of application.

PRIMING

UC-190 SRX does not normally require a primer due to the application method unless the substrate is extremely porous. If a primer is needed, a scratch coat of UC-190 SRX is recommended.

MIXING EQUIPMENT

Low speed drill and 3" Jiffler Mixer or Hanson Plunge Mixer.

Important: Hand mixing will produce inconsistent results and is not an approved method.

MIXING

Thoroughly mix each component separately before combining. Pour the base (Part A) and hardener (Part B) components together in a clean, dry 5-gallon (18.93 L) container and power mix using a 3" (7.6 cm) Jiffler Mixer or Hanson Plunge Mixer. While mixing, slowly add filler (Part C) and Pigment Pack (Part D) and continue to mix until uniform color is achieved. Pigment Pack optional if using color quartz.

DO NOT THIN



UC-190 SRX

URETHANE CEMENT

PRODUCT APPLICATION (cont.)

APPLICATION EQUIPMENT

Steel hand trowel or adjustable screed pin or cam rake
Spiked or looped roller

APPLICATION

Immediately after mixing, spread the UC-190 SRX using a steel hand trowel or adjustable screed rake set to the desired thickness. Immediately roll with a spiked or looped roller to release any entrapped air and level the mortar. Do not roll the surface after 4 to 8 minutes of it being applied to the floor. Late rolling will cause problems with the finished texture and appearance.

Broadcast #20-40 quartz aggregate or color quartz aggregate to rejection, approximately 1 lb. per square foot.

CLEAN UP

Applicators and equipment should be cleaned immediately after use with an active solvent like xylene (in SCAQMD, use acetone only). Clean spills or drips while still wet with solvent. Dried UC-190 SRX will require mechanical abrasion for removal.

PERFORMANCE CHARACTERISTICS

COMPRESSIVE STRENGTH

METHOD: ASTM C579
RESULT: 8,128 psi

TENSILE STRENGTH

METHOD: ASTM C307
RESULT: 1,450 psi

BOND STRENGTH TO CONCRETE

METHOD: ASTM D4541
RESULT: Minimum 400 psi (100% concrete failure)

FLEXURAL STRENGTH

METHOD: ASTM C580
RESULT: 2,900 psi (20 MPa)

ABRASION RESISTANCE

METHOD: ASTM D4060 (CS 17 wheels, 1000 cycles)
RESULT: 0.05g loss

COEFFICIENT OF THERMAL EXPANSION

METHOD: ASTM C531
RESULT: 1.5×10^{-5} in/in/°F

COEFFICIENT FRICTION

METHOD: ASTM D2047
RESULT: Exceeds ADA recommendations

TEMPERATURE RESISTANCE

METHOD: Continuous exposure
RESULT: 200°F

METHOD: Intermittent spills
RESULT: 250°F

**TECHNICAL DATA****CDL-61****UC-190 SRX
URETHANE CEMENT****PHYSICAL PROPERTIES**

		UC-190 SRX
Resin Type		Cementitious Urethane
Pigment Type		Varies depending on color
Weight	Per Gallon	8.4-10.2 lbs.
	Per Liter	1.0-1.2 kg
Solids	By Weight	100%
	By Volume	100%
Volatile Organic Compounds		<10 g/l
Recommended Dry Film Thickness (DFT) Per Coat		190 mils
Practical Coverage		40 sq ft/kit at 3/16" (yielding a 1/4" finished floor) 30 sq ft/kit at 1/4" (yielding 5/16" finished floor)
Mixing Ratio		1 Container Part A : 1 Container Part B : 1 Bag Filler : 1 Pigment Pack
Pot Life @ 70°F (21°C) and 50% Relative Humidity		20-25 minutes
Re-Coat Window (Min./Max)		12 hours/24 hours
Dry Times at 77°F (25°C) and 50% Relative Humidity	Foot Traffic	6-8 hours
	Vehicle Traffic	12-16 hours
	Full Cure*	3-5 days
Dry Heat Resistance		250°F (121°C)
Shelf Life		2 years
Flash Point		>350°F (>176°C)
Safety Information		For additional information, see SDS

*Coating achieves its full physical and chemical resistant properties.
Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Citadel Floor Finishing Systems
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 800-962-3099
www.citadelfloors.com

Form: EJ-310
Rev.: 102125